

Water Chemistry for Cement-based Adhesives, Waterproofing Membranes and Grouts in Tiled Swimming Pools

Maintaining the water chemistry of a pool is the responsibility of the pool owner.

Introduction and Scope

This information sheet provides an initial understanding of the effect some of the chemicals used in swimming pool water have on cement-based adhesives and grouts used with ceramic tile finishes. The traditional chemicals of concern are the Calcium based and the Sulphate based compounds that affect the mineralogy of the tile grouts and adhesives.

However, in recent times we have observed some unusual problems with cement-based grout in pools containing Magnesium Chloride (instead of normal salt – Sodium Chloride). We note also water treated with 'mineral salts' containing unusual trace elements.

While this information sheet is primarily related to tile finishes in immersed conditions, overflow and frequent wetting in the adjacent splash zones around pools may also show these effects.

Calcium Hardness

Hardness is said to be a measure of the Calcium and Magnesium dissolved in the water.

Pool water is said to be **hard and non-aggressive** when the Calcium level (expressed as Calcium Carbonate) exceeds, or can be maintained at over 200mg/L. In this situation Calcium is **not leached** from cement-based materials and the tile adhesives and grouts will remain in good condition.

Where the pool water has low (<90 mg/L) Calcium levels, it is said to be **soft and aggressive** towards cement-based materials. Calcium may be leached from the tile adhesives and grouts to such an extent that the grout is removed from joints between tiles and the tile adhesives may be weakened sufficiently to allow debonding of tiles.

High levels of Calcium may lead to lime scale (Calcium carbonate) deposits building up in the pool plumbing system. To prevent these deposits occurring, the pool water Calcium hardness levels have been recommended to be in the range 90-200 mg/L.

It has been noted that when the water has low Calcium hardness and low bicarbonate alkalinity levels, the pH value may still be high (indicating overall alkaline conditions) and the water is still aggressive to cement based products. This may be corrected by using a water treatment that adds Calcium salts to the water.

The water supply in most Australian cities is soft, except in Perth, Adelaide and some country areas. Melbourne water is said to be particularly soft. The importance of correctly maintaining the pool water chemistry should always include the Calcium and Sulphate chemistry.

The Sulphate Effect

The effects of soluble Sulphates on cement-based mortars and grouts are dependent on the Sulphate concentration. BS 5385.4 - 2015 states that the maximum permitted concentration of soluble Sulphates is 300 mg/L (expressed as SO₃ equivalent to 360 mg/L SO₄).

Sulphate weakens cement-based products by changing the original cement crystalline form to an expanded, mechanically weaker crystalline form. This leads to deterioration within the cement-based grouts as the expanded structure becomes more susceptible to chemical attack and physical stress.

Cement-based products form strong bonds to the substrate and within adhesives and mortars by reacting (hydrating) with water and forming crystals that lock into the pores at the substrate

(concrete) surface or interlock with each other in mortars and adhesives. These crystals may be considered as mechanical anchors and the bonding formed is very strong. Chemical alteration by the sulphates in the pool water changes these crystals to long thin needle-like shapes that are weaker than the original crystalline shapes.

Where both low concentrations of Calcium compounds and high concentrations of Sulphates occur, the corrosion effect is accelerated.

Acidity

The pH is a measure of the acidity or alkalinity of pool water and the ideal value is 7.5 with the normal range between 7.2 and 7.8. The scale ranges from 0 to 14 where acidic conditions are indicated at low values below 7, and alkaline conditions are indicated by high values above 7. The value 7 is set at the reading of pure water, which is said to be neutral, neither acidic nor alkaline. The pH may vary in a pool with the effects being sore eyes or itchiness, accelerated corrosion and possibly scale formation, reduced effectiveness of Chlorine sanitisers and increased cloudiness of the water, especially when the pH is below 6.8 or above 8.5.

The importance of the pool water pH is that it is an indicator of the pool quality and how some of the pool chemicals will be acting. To raise the pH, the procedure is to normally add Sodium Carbonate or Bi-Carbonate, and to lower the pH, add Sodium Bisulphate or Hydrochloric Acid. Repeated additions of the Bi-Sulphate will lead to the chemical attack on the cement-based adhesives and grouts previously noted above. However, low levels of Calcium in the pool water are not indicated by the pH readings as previously noted.

Magnesium and Other Elements

Some pools are treated with minerals other than common salt (i.e. sea salt) as the source of Chloride for the effective action of the electrolytic converters to generate free Chlorine. Whilst these treatments won't affect polymer shell pools to our knowledge, the 'jury is out' on the effect they can have on cementitious grouts and adhesives.

Magnesium

One type of mineral treatment uses Magnesium Chloride instead of, or with Sodium Chloride (common sea salt). The issue with Magnesium relates to its chemical similarity to Calcium in terms of compounds formed. The Magnesium substitutes for Calcium in minerals which form the hardened cement paste matrix, and this change results in weakening of the material. It is a recognised situation, that Magnesium salts can damage cementitious containing materials such as concrete and we have noted that pools containing high levels of Magnesium Chloride appear to be linked with instances of powdery cement-based grout. In lieu of this apparent situation we recommend that non-cementitious R Class grout materials are used in pools treated in this way.

Boron

Pool water can be treated with water chemicals containing compounds of Boron, sometimes as a pH buffer at a concentration of less than 200ppm, but for other claimed reasons too. It also has properties for ion exchange and reducing water hardness. Otherwise, this is an uncommon element in normal household environments, and is probably best known for uses as a disinfectant, wood preservative, fire retardant and insecticide.

However, it is common in the nuclear industry, and literature related to the compounds of this element in the nuclear waste industry suggest that Boron compounds inhibit the cure of Portland cement-based systems for waste encapsulation. We know that improperly cured cement can have compromised properties, therefore in the absence of any hard data re pool issues, we would recommend cementitious materials used in pools treated in this way are well cured before any Boron containing material is added (i.e. at least 21 days dry cure as per AS3958).

Chlorine

This element is the water purification medium to keep the pool free of algae and other harmful organisms like bacteria. High levels of free Chlorine apart from being an irritant to swimmers, also can create changes in materials such as grouts. Particularly if coloured or pigmented grouts are used, the Chlorine bleaches the colour rendering the grouts a neutral whitish colour. Notably the grout above and below the waterline can end up being different shades or even appearing to be different colours.

Recommendations

The recommended water chemistry balance in **pools with ceramic tile finishes using common water treatment** (dry or tablet Chlorine, common salt, and water treated with UV or Ozone) is as follows:

Required

Total Alkalinity range recommended	80 - 200 mg/L
pH range	7.2 - 7.8
Calcium Hardness range	150 - 200 mg/L
Sulphate range	< 200 mg/L

Other typical values

Chlorine (free)	~1 - 2ppm
Salt as Sodium Chloride (saltwater pools)	~4000 - 6000ppm

While these values may be slightly different to what many operators would regard as normal, we emphasise that these values are related to ceramic tile finishes that have been fixed (adhered) and grouted with cement-based products. The values given here are in the recommended ranges to prevent corrosion of the cement in the adhesives and grouts.

The Australian Standard references do include the information regarding the effects of the chemical compounds noted in this technical bulletin. However, those standards also apply to other types of pool finishes and care must be taken to ensure that the appropriate range is used in tiled pools.

We would also advise that excessively high levels of Chlorine can have a negative impact on cement-based materials, and Brominated materials as used in spas are very aggressive and attack grouts and adhesives.

Non-Standard Pool Treatments

The increasing use of epoxy-based grouts is noted as pool operators see the effects of 'out of balance pool water' and make use of the chemical resistance of epoxy R Class grouts.

Standards Documents

The guidelines for pool water published by Standards Australia currently used are:

- GB65 - 1998 Residential Swimming Pools – selection, maintenance operation (originally published as HB65-1998);
- HB241 - 2002 Water Management for Public Swimming Pools and Spas

Glossary

Alkalinity - Refers to the presence of soluble alkaline materials that are included in the pool water to buffer it against acidity. Typical alkalinity modifiers are Sodium Carbonate ('washing soda') or Sodium Bicarbonate ('bicarb' or 'bicarb of soda'). Where the alkalinity rises too high, the pH also rises, and Calcium compounds start to precipitate as scum lines.

Boron - This refers to compounds of Boron such as Borax (hydrated Boron Oxide) or Boric Acid.

C-Class - This refers to cementitious based adhesives and grouts as defined in ISO13007. The cement is normally ordinary Portland cement (OPC).

Calcium - This is a shorthand for compounds of Calcium such as Calcium Carbonate ('lime scale').

Calcium Hardness - Is another form of shorthand to describe the concentration of Calcium and Magnesium compounds in the water (the two are treated as one combined entity). The hardness is controlled by soluble or partially soluble Calcium and Magnesium compounds (present as Carbonate and Bicarbonate) levels and pH.

Chlorine - In pools it is present as free Chlorine, but is added as a Hypochlorite compound, Cyano-chlorine compound or is generated by electrolytic background of Chloride salts such as Sodium Chloride (common or sea salt).

Hard water - Contains high concentrations of Calcium and Magnesium compounds, usually Calcium and/or Magnesium Carbonate. These metal cations are relatively insoluble so as Carbonates and so it is relatively easy to have hard water where they are available. Typically, water obtained from limestone source areas is 'hard'. Note that water can have high alkalinity, but low or high hardness.

Magnesium - In this case, this is shorthand for Magnesium Chloride, but can also apply to the more aggressive Magnesium Sulphate (also called Epsom salts).

pH - This is unit of measurement to indicate whether the water is acid, alkaline or neutral. The range is 0-14 with tap water having a range 6.7 to 7.4 for most cases. pH is defined as a measure of the concentration of acid (H+) or alkali (usually expressed as OH-) in the water. Alkaline water containing Carbonates is more complex measurement. At pH 7 the water is neutral and the acid and alkali counterbalance each other - $H^+ + OH^- = H_2O$. Distilled water is neutral.

R Class - This refers to adhesives and grouts composed of reaction polymers as defined in ISO13007. The typical R class materials are based on epoxy resin.

Soft water - Contains low levels of Calcium or Magnesium salts. Sodium Carbonate was traditionally used to soften hard water for washing purposes—hence the name 'washing soda'. Soft water is required for soaps to work correctly. In a concrete pool situation, where the water is too soft, it will scavenge Calcium from the cementitious components in the pool (i.e. concrete shell, grouts and tile adhesives) which over time damages the cement base in these items.

Sulphate - Spelled as Sulfate in American usages. This is an anion based around the parent compound Sulphuric Acid. Common Sulphates are Sodium Sulphate and Sodium Bisulphate which can be used acidifiers, or Aluminium Sulphate ('Alum' used for clarifying the water). Sulphate in pool water can attack the cement components in a pool, damaging them by forming Calcium and Magnesium Sulphate (gypsum and 'Epsom Salts') and also corroding metal fixtures.



Adelaide (08) 8243 7888 **Sydney** (02) 9756 3533
Brisbane (07) 3271 2944 **Auckland** (09) 273 5444
Melbourne (03) 9761 4711 **Kuala Lumpur** (603) 5122 2522
Perth (08) 9356 9999

www.constructionchemicals.com.au

The information contained in this technical publication is based on our current knowledge and experience and is provided as a guide only. In view of the many factors that may affect application it is the user's sole responsibility to ensure suitability for a specific purpose.